



SPECTRUM GREEN 40 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	41
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	25
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	68
SHADING COEFFICIENT	0.52
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	55
% GLARE REDUCTION	55

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SPECTRUM GREEN 50 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	52
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	33
% SOLAR REFLECTANCE	5
% SOLAR ABSORBANCE	62
SHADING COEFFICIENT	0.59
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	49
% GLARE REDUCTION	43

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SPECTRUM GREEN 60 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	61
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	33
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	60
SHADING COEFFICIENT	0.57
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	50
% GLARE REDUCTION	33

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SPECTRUM GREEN 70 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	69
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	46
% SOLAR REFLECTANCE	5
% SOLAR ABSORBANCE	49
SHADING COEFFICIENT	0.70
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	40
% GLARE REDUCTION	24

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SPECTRUM GREEN 80 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	78
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	57
% SOLAR REFLECTANCE	5
% SOLAR ABSORBANCE	38
SHADING COEFFICIENT	0.79
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	32
% GLARE REDUCTION	14

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SPECTRUM GREY 40 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	40
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	21
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	73
SHADING COEFFICIENT	0.48
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	59
% GLARE REDUCTION	56

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SPECTRUM GREY 50 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	51
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	26
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	67
SHADING COEFFICIENT	0.50
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	55
% GLARE REDUCTION	44

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SPECTRUM GREY 60 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	60
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	31
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	62
SHADING COEFFICIENT	0.55
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	52
% GLARE REDUCTION	34

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SPECTRUM GREY 70 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	69
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	35
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	56
SHADING COEFFICIENT	0.59
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	49
% GLARE REDUCTION	24

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SPECTRUM GREY 80 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	79
% VISIBLE LIGHT REFLECTANCE	9
% SOLAR TRANSMITTANCE	47
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	46
SHADING COEFFICIENT	0.69
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	40
% GLARE REDUCTION	13

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



XP CHARCOAL 20 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	22
% VISIBLE LIGHT REFLECTANCE	15
% SOLAR TRANSMITTANCE	16
% SOLAR REFLECTANCE	15
% SOLAR ABSORBANCE	69
SHADING COEFFICIENT	0.41
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	65
% GLARE REDUCTION	76

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



XP CHARCOAL 30 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	28
% VISIBLE LIGHT REFLECTANCE	11
% SOLAR TRANSMITTANCE	21
% SOLAR REFLECTANCE	12
% SOLAR ABSORBANCE	67
SHADING COEFFICIENT	0.45
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	61
% GLARE REDUCTION	69

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



IR 80 CERAMIC

THICKNESS OF FILM (MIL)	1
% VISIBLE LIGHT TRANSMITTANCE	77
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	61
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	32
SHADING COEFFICIENT	0.80
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	30
% GLARE REDUCTION	13

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP CHARCOAL 05 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	4
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	18
% SOLAR REFLECTANCE	22
% SOLAR ABSORBANCE	60
SHADING COEFFICIENT	0.46
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	65
% GLARE REDUCTION	96

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP CHARCOAL 10 METALLIZED

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	10
% VISIBLE LIGHT REFLECTANCE	5
% SOLAR TRANSMITTANCE	29
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	63
SHADING COEFFICIENT	0.54
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	53
% GLARE REDUCTION	89

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP CHARCOAL 15 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	16
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	19
% SOLAR REFLECTANCE	22
% SOLAR ABSORBANCE	59
SHADING COEFFICIENT	0.39
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	61
% GLARE REDUCTION	82

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP CHARCOAL 20 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	21
% VISIBLE LIGHT REFLECTANCE	10
% SOLAR TRANSMITTANCE	24
% SOLAR REFLECTANCE	23
% SOLAR ABSORBANCE	53
SHADING COEFFICIENT	0.45
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	58
% GLARE REDUCTION	76

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP CHARCOAL 35 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	39
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	43
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	49
SHADING COEFFICIENT	0.66
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	43
% GLARE REDUCTION	57

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP CHARCOAL 50 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	54
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	57
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	35
SHADING COEFFICIENT	0.77
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	37
% GLARE REDUCTION	40

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP BLUE 35 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	41
% VISIBLE LIGHT REFLECTANCE	19
% SOLAR TRANSMITTANCE	48
% SOLAR REFLECTANCE	16
% SOLAR ABSORBANCE	36
SHADING COEFFICIENT	0.70
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	44
% GLARE REDUCTION	54

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP GREEN 30 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	37
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	41
% SOLAR REFLECTANCE	9
% SOLAR ABSORBANCE	50
SHADING COEFFICIENT	0.63
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	40
% GLARE REDUCTION	58

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP GREY 20 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	22
% VISIBLE LIGHT REFLECTANCE	9
% SOLAR TRANSMITTANCE	25
% SOLAR REFLECTANCE	23
% SOLAR ABSORBANCE	52
SHADING COEFFICIENT	0.49
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	58
% GLARE REDUCTION	75

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP GREY 35 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	36
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	42
% SOLAR REFLECTANCE	9
% SOLAR ABSORBANCE	49
SHADING COEFFICIENT	0.63
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	46
% GLARE REDUCTION	60

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP ONYX 05 METALLIZED

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	4
% VISIBLE LIGHT REFLECTANCE	5
% SOLAR TRANSMITTANCE	32
% SOLAR REFLECTANCE	11
% SOLAR ABSORBANCE	57
SHADING COEFFICIENT	0.45
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	52
% GLARE REDUCTION	97

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP ONYX 15 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	14
% VISIBLE LIGHT REFLECTANCE	5
% SOLAR TRANSMITTANCE	35
% SOLAR REFLECTANCE	11
% SOLAR ABSORBANCE	54
SHADING COEFFICIENT	0.51
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	50
% GLARE REDUCTION	88

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.

www.armolan.com



HP ONYX 35 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	32
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	46
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	46
SHADING COEFFICIENT	0.65
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	35
% GLARE REDUCTION	70

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



HP ONYX 50 METALLIZED

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	34
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	50
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	44
SHADING COEFFICIENT	0.65
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	35
% GLARE REDUCTION	70

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR CHARCOAL 05 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	6
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	45
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	48
SHADING COEFFICIENT	0.67
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	33
% GLARE REDUCTION	93

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR CHARCOAL 20 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	21
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	48
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	46
SHADING COEFFICIENT	0.71
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	29
% GLARE REDUCTION	77

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR CHARCOAL 30 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	30
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	50
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	43
SHADING COEFFICIENT	0.72
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	28
% GLARE REDUCTION	67

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR CHARCOAL 35 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	36
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	52
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	41
SHADING COEFFICIENT	0.73
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	27
% GLARE REDUCTION	60

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR CHARCOAL 40 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	39
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	56
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	38
SHADING COEFFICIENT	0.77
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	33
% GLARE REDUCTION	57

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR CHARCOAL 50 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	52
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	63
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	31
SHADING COEFFICIENT	0.82
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	18
% GLARE REDUCTION	42

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR ONYX PREMIUM 05 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1.5
% VISIBLE LIGHT TRANSMITTANCE	6
% VISIBLE LIGHT REFLECTANCE	4
% SOLAR TRANSMITTANCE	42
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	52
SHADING COEFFICIENT	0.64
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	44
% GLARE REDUCTION	94

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR ONYX PREMIUM 20 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1
% VISIBLE LIGHT TRANSMITTANCE	13
% VISIBLE LIGHT REFLECTANCE	5
% SOLAR TRANSMITTANCE	47
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	47
SHADING COEFFICIENT	0.69
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	40
% GLARE REDUCTION	85

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR ONYX PREMIUM 35 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1
% VISIBLE LIGHT TRANSMITTANCE	32
% VISIBLE LIGHT REFLECTANCE	5
% SOLAR TRANSMITTANCE	57
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	37
SHADING COEFFICIENT	0.77
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	33
% GLARE REDUCTION	67

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR ONYX PREMIUM 50 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	1
% VISIBLE LIGHT TRANSMITTANCE	48
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	61
% SOLAR REFLECTANCE	5
% SOLAR ABSORBANCE	34
SHADING COEFFICIENT	0.76
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	28
% GLARE REDUCTION	55

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR BLUE 35 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	38
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	55
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	38
SHADING COEFFICIENT	0.76
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	34
% GLARE REDUCTION	58

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR BRONZE 35 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	32
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	56
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	37
SHADING COEFFICIENT	0.77
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	33
% GLARE REDUCTION	64

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR GREEN 20 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	22
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	48
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	46
SHADING COEFFICIENT	0.72
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	39
% GLARE REDUCTION	75

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR GREEN 35 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	37
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	55
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	38
SHADING COEFFICIENT	0.76
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	33
% GLARE REDUCTION	58

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 15 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	15
% VISIBLE LIGHT REFLECTANCE	68
% SOLAR TRANSMITTANCE	12
% SOLAR REFLECTANCE	56
% SOLAR ABSORBANCE	32
SHADING COEFFICIENT	0.24
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	79
% GLARE REDUCTION	84

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 20 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	17
% VISIBLE LIGHT REFLECTANCE	55
% SOLAR TRANSMITTANCE	12
% SOLAR REFLECTANCE	49
% SOLAR ABSORBANCE	38
SHADING COEFFICIENT	0.26
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	78
% GLARE REDUCTION	81

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 35 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	41
% VISIBLE LIGHT REFLECTANCE	29
% SOLAR TRANSMITTANCE	31
% SOLAR REFLECTANCE	27
% SOLAR ABSORBANCE	41
SHADING COEFFICIENT	0.49
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	58
% GLARE REDUCTION	55

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 50 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	55
% VISIBLE LIGHT REFLECTANCE	24
% SOLAR TRANSMITTANCE	43
% SOLAR REFLECTANCE	24
% SOLAR ABSORBANCE	33
SHADING COEFFICIENT	0.60
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	48
% GLARE REDUCTION	39

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 70 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	69
% VISIBLE LIGHT REFLECTANCE	12
% SOLAR TRANSMITTANCE	56
% SOLAR REFLECTANCE	12
% SOLAR ABSORBANCE	32
SHADING COEFFICIENT	0.75
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	35
% GLARE REDUCTION	23

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R GREY 10 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	8
% VISIBLE LIGHT REFLECTANCE	18
% SOLAR TRANSMITTANCE	9
% SOLAR REFLECTANCE	57
% SOLAR ABSORBANCE	34
SHADING COEFFICIENT	0.26
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	76
% GLARE REDUCTION	91

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R BRONZE 10 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	10
% VISIBLE LIGHT REFLECTANCE	25
% SOLAR TRANSMITTANCE	8
% SOLAR REFLECTANCE	39
% SOLAR ABSORBANCE	53
SHADING COEFFICIENT	0.24
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	79
% GLARE REDUCTION	89

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R BLUE 15 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	13
% VISIBLE LIGHT REFLECTANCE	31
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	37
% SOLAR ABSORBANCE	52
SHADING COEFFICIENT	0.29
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	75
% GLARE REDUCTION	86

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R GOLD 15 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	14
% VISIBLE LIGHT REFLECTANCE	52
% SOLAR TRANSMITTANCE	13
% SOLAR REFLECTANCE	53
% SOLAR ABSORBANCE	34
SHADING COEFFICIENT	0.25
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	78
% GLARE REDUCTION	84

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NF SOLAR BRONZE 20

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	18
% VISIBLE LIGHT REFLECTANCE	46
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	62
% SOLAR ABSORBANCE	27
SHADING COEFFICIENT	0.24
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	79
% GLARE REDUCTION	80

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NF SOLAR BRONZE 35

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	33
% VISIBLE LIGHT REFLECTANCE	32
% SOLAR TRANSMITTANCE	21
% SOLAR REFLECTANCE	50
% SOLAR ABSORBANCE	29
SHADING COEFFICIENT	0.31
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	73
% GLARE REDUCTION	63

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 20 EXTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	17
% VISIBLE LIGHT REFLECTANCE	55
% SOLAR TRANSMITTANCE	12
% SOLAR REFLECTANCE	49
% SOLAR ABSORBANCE	38
SHADING COEFFICIENT	0.26
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	78
% GLARE REDUCTION	81

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 35 EXTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	41
% VISIBLE LIGHT REFLECTANCE	29
% SOLAR TRANSMITTANCE	31
% SOLAR REFLECTANCE	27
% SOLAR ABSORBANCE	41
SHADING COEFFICIENT	0.49
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	58
% GLARE REDUCTION	55

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 50 EXTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	55
% VISIBLE LIGHT REFLECTANCE	24
% SOLAR TRANSMITTANCE	43
% SOLAR REFLECTANCE	24
% SOLAR ABSORBANCE	33
SHADING COEFFICIENT	0.60
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	48
% GLARE REDUCTION	39

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R GREY 10 EXTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	8
% VISIBLE LIGHT REFLECTANCE	18
% SOLAR TRANSMITTANCE	9
% SOLAR REFLECTANCE	57
% SOLAR ABSORBANCE	34
SHADING COEFFICIENT	0.26
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	76
% GLARE REDUCTION	91

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R BRONZE 10 EXTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	10
% VISIBLE LIGHT REFLECTANCE	25
% SOLAR TRANSMITTANCE	8
% SOLAR REFLECTANCE	39
% SOLAR ABSORBANCE	53
SHADING COEFFICIENT	0.24
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	79
% GLARE REDUCTION	89

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R BLUE 15 EXTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	13
% VISIBLE LIGHT REFLECTANCE	31
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	37
% SOLAR ABSORBANCE	52
SHADING COEFFICIENT	0.29
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	75
% GLARE REDUCTION	86

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



POLY SILVER 15 FOR POLYCARBONATE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	14
% VISIBLE LIGHT REFLECTANCE	72
% SOLAR TRANSMITTANCE	10
% SOLAR REFLECTANCE	72
% SOLAR ABSORBANCE	18
SHADING COEFFICIENT	0.18
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	83
% GLARE REDUCTION	85

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



UV 2MIL CLEAR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	89
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	81
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	13
SHADING COEFFICIENT	0.98
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	15
% GLARE REDUCTION	2

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



WHITE MATTE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	66
% VISIBLE LIGHT REFLECTANCE	22
% SOLAR TRANSMITTANCE	60
% SOLAR REFLECTANCE	18
% SOLAR ABSORBANCE	22
SHADING COEFFICIENT	0.76
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	19
% GLARE REDUCTION	28

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SILVER MATTE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	13
% VISIBLE LIGHT REFLECTANCE	62
% SOLAR TRANSMITTANCE	14
% SOLAR REFLECTANCE	56
% SOLAR ABSORBANCE	30
SHADING COEFFICIENT	0.25
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	75
% GLARE REDUCTION	86

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



GREY MATTE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	36
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	55
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	38
SHADING COEFFICIENT	0.78
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	22
% GLARE REDUCTION	60

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



BRONZE MATTE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	35
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	56
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	38
SHADING COEFFICIENT	0.77
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	23
% GLARE REDUCTION	61

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



WHITE OUT

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	8
% VISIBLE LIGHT REFLECTANCE	59
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	47
% SOLAR ABSORBANCE	41
SHADING COEFFICIENT	0.27
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	77
% GLARE REDUCTION	91

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



BLACK OUT

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	0
% VISIBLE LIGHT REFLECTANCE	5
% SOLAR TRANSMITTANCE	0
% SOLAR REFLECTANCE	34
% SOLAR ABSORBANCE	66
SHADING COEFFICIENT	0.21
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	82
% GLARE REDUCTION	100

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 2 MIL CLEAR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	87
% VISIBLE LIGHT REFLECTANCE	9
% SOLAR TRANSMITTANCE	83
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	9
SHADING COEFFICIENT	0.9
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	2
% GLARE REDUCTION	1

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 4 MIL CLEAR

THICKNESS OF FILM (MIL)	4
% VISIBLE LIGHT TRANSMITTANCE	87
% VISIBLE LIGHT REFLECTANCE	9
% SOLAR TRANSMITTANCE	79
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	13
SHADING COEFFICIENT	0.96
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	2
% GLARE REDUCTION	1

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 7 MIL CLEAR

THICKNESS OF FILM (MIL)	7
% VISIBLE LIGHT TRANSMITTANCE	87
% VISIBLE LIGHT REFLECTANCE	10
% SOLAR TRANSMITTANCE	79
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	13
SHADING COEFFICIENT	0.95
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	2
% GLARE REDUCTION	0

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 12 MIL CLEAR

THICKNESS OF FILM (MIL)	12
% VISIBLE LIGHT TRANSMITTANCE	87
% VISIBLE LIGHT REFLECTANCE	10
% SOLAR TRANSMITTANCE	78
% SOLAR REFLECTANCE	9
% SOLAR ABSORBANCE	13
SHADING COEFFICIENT	0.95
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	4
% GLARE REDUCTION	2

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



ULTIMATE 05 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	5
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	5
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	89
SHADING COEFFICIENT	0.34
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	70
% GLARE REDUCTION	94

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



ULTIMATE 20 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	20
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	82
SHADING COEFFICIENT	0.39
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	66
% GLARE REDUCTION	78

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



ULTIMATE 35 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	41
% VISIBLE LIGHT REFLECTANCE	9
% SOLAR TRANSMITTANCE	21
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	71
SHADING COEFFICIENT	0.47
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	59
% GLARE REDUCTION	55

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



ULTIMATE 50 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	51
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	25
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	67
SHADING COEFFICIENT	0.50
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	56
% GLARE REDUCTION	44

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



XP CHARCOAL 05 CERAMIC

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	5
% VISIBLE LIGHT REFLECTANCE	8
% SOLAR TRANSMITTANCE	10
% SOLAR REFLECTANCE	14
% SOLAR ABSORBANCE	76
SHADING COEFFICIENT	0.35
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	69
% GLARE REDUCTION	94

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.